T > +31 (0)85 060 58 49

E > info@liqcreate.com

l > www.liqcreate.com

## Liqcreate Clear Impact

A durable and easy to print stereolithography (SLA) and Digital Light Processing (DLP) material that allows expansion into new prototype and end-use applications.

#### **Product description**

Liqcreate Clear Impact is an optically clear photopolymer for SLA and DLP technologies in the range of 385 - 405nm. Parts created with Liqcreate Clear Impact are perfectly transparent, slightly flexible and have an excellent impact resistance.

The high toughness of the material makes it ideal for the production of functional parts which are repeatedly exposed to stress. Low water absorption and weather resistance makes it perfect for outdoor applications.

### Key benefits

- Optically clear
- Excellent Impact resistance
- Good water and chemical resistance
- Low yellowing

### 3D-Printer compatibility

- Moonray S & D
- Miicraft 125
- Form2
- Peopoly Moai
- Asiga Max, PRO
- Cubicon Lux HD
- Anycubic Photon
- All open source 385 405nm SLA and DLP 3D-printers

#### Order information

Order directly on <a href="www.liqcreate.com/store">www.liqcreate.com/store</a> or send your inquiry with the following order numbers to order@liqcreate.com.

Liqcreate Clear Impact 250gram Liqcreate Clear Impact 1 kg Order number LCI00250 Order number LCI01000



T > +31 (0)85 060 58 49

E > info@liqcreate.com

l > www.liqcreate.com

# Liqcreate Clear Impact Technical Data

Liquid properties				
Appearance	Colorless clear liquid	E <sub>C</sub>	9.88 mJ/cm <sup>2</sup>	
Viscosity	1000 cps at 25°C	D <sub>p</sub> metric	0.20 mm	
Density	1.12 g/cm <sup>2</sup>	D <sub>p</sub> imperial	7.87 mils	

Polymer properties				
Mechanical properties		10 minutes high power mercury curing		
Description	ASTM Method	Metric	Imperial	
Tensile Strength	D638M	45 MPa	6.5 ksi	
Tensile Modulus	D638M	1.4 MPa	203 ksi	
Elongation at break	D638M	25%		
Flexural Strength	D790M	35 MPa	5.1 ksi	
Flexural modulus	D2240	900 MPa	131 ksi	
IZOD Impact (notched)	D256A	31 J/m	0.75 ft-lb/in	
Shore D Hardness	D2240	68		
Water sorption	D570-98	0.50%		
Tg	D7028	32°C	90°F	

These values may vary and depend on individual machine processing and post-curing.

Visit <a href="www.liqcreate.com">www.liqcreate.com</a> for more information about this product.