

# LIQCREATE



T > +31 (0)85 060 58 49  
E > [info@liqcreate.com](mailto:info@liqcreate.com)  
I > [www.liqcreate.com](http://www.liqcreate.com)

## User's guide Liqcreate® Premium White

Liqcreate Premium White is an opaque white photopolymer with excellent UV-stability. 3D-printed parts from this material show no discoloration and stay perfectly white, even after long-term UV exposure. Liqcreate Premium White is easy to use on all open source LCD and DLP 3D-printers in the range of 385 - 420nm. This material has excellent properties like low shrinkage and low odor, which makes it ideal for the production of medical models, architectural scale models and miniatures.

This User's Guide provides useful information to get the best experience from our product, Liqcreate Premium White. This includes handling of the materials, safety and parameters for several 3D-printers.












## Table of content

1. General information .....	1
2. Resin Handling .....	1
3. Compatibility 3D-printers .....	2
4. Build parameters .....	<b>Fout! Bladwijzer niet gedefinieerd.</b>
4.1. Wanhao Duplicator 7 .....	2
4.2. Anycubic Photon .....	3
4.3. Kudo3D Bean .....	3
4.4. Phrozen Shuffle .....	3
5. Post-processing .....	4
5.1. Spill cleaning protocol .....	4
6. Safety .....	4
7. Storage and transport .....	4
8. Plastic and Packaging Waste .....	4



## 1. General information

Liqcreate Premium White is part of our Premium LCD photopolymer family. This User's Guide contains useful information to get started with this resin. The table below explains all signs on the label.

Label Signs	Definition
	Liquid waste and contaminated towels should be treated as chemical waste
	Keep bottles and resin out of direct (sun) light
	Resin and packaging should not be stored below 5°C or above 30°C for a longer period
	This bottle contains 1000 grams or 250 grams of resin when un-used
	This resin is designed to be printed at 25 to 100 micron layer thickness. More information on printing parameters is mentioned in chapter 4
	Shake bottles properly before use.
	This resin is designed to be printed on both LCD (Liquid Crystal Display) and DLP (projection based) 3D-printers. Ideally within the range of 385-420 nm

## 2. Resin Handling

Shake the bottle for at least 1 minute before use. After shaking leave the resin to rest for 10 minutes to let air bubbles escape. The resin can be poured back into the bottle after use. Check the resin for residual pieces of polymer before pouring back the resin in the bottle. Always use protective measures when handling Liqcreate resins. Extended safety instructions can be found in the safety data sheet.



### 3. Compatibility 3D-printers

Liqcreate Premium White is a photopolymer designed for LCD and DLP technologies in the range of 385 to 420 nm. Several 3D-printers are already compatible with Liqcreate Premium White, these include the Wanhao D7, Anycubic Photon, Kudo3D Bean and the Phrozen shuffle. Contact our experts at [info@liqcreate.com](mailto:info@liqcreate.com) for settings on other 3D-printers.

#### 3.1. Wanhao Duplicator 7

Printing parameters for Liqcreate Premium White are shown in the table and image below.

Slice Thickness (mm)	Exposure Time (ms)	Bottom Exposure time (ms)	# Bottom Layers
0.100	11 000	160 000	2
0.050	9 000	160 000	2
0.035	7 000	160 000	2

Help
Apply Changes

**Settings**

Slice Thickness (mm)

Exposure Time (ms)

Bottom Exposure (ms)

# Bottom Layers

Enable Anti-Aliasing

Enable Slice Outlines

Outline Width Inset (pix)

Outline Width Outset (pix)

**Image Reflection**

Reflect X  Reflect Y

**Lift and Sequence**

Lift and Sequence Time (ms)  Auto Calc

Z Lift Distance (mm)

Z Lift Speed (mm/m)

Z Bottom Speed (mm/m)

Z Retract Speed (mm/m)

Slide / Tilt Value

Build Direction

**Export Options**

Export to CWS  Export to Disk

Export SVG:

Export Preview:



### 3.2. Anycubic Photon

Printing parameters for Liqcreate Premium White are shown in the image below.

Layer thickness(mm): <input type="text" value="0.035"/>	Layer thickness(mm): <input type="text" value="0.05"/>	Layer thickness(mm): <input type="text" value="0.1"/>
Normal exposure time (s): <input type="text" value="7"/>	Normal exposure time (s): <input type="text" value="9"/>	Normal exposure time (s): <input type="text" value="11"/>
Off time (s): <input type="text" value="2"/>	Off time (s): <input type="text" value="2"/>	Off time (s): <input type="text" value="2"/>
Bottom Exposure Time (s): <input type="text" value="60"/>	Bottom Exposure Time (s): <input type="text" value="60"/>	Bottom Exposure Time (s): <input type="text" value="60"/>
Bottom layers: <input type="text" value="8"/>	Bottom layers: <input type="text" value="8"/>	Bottom layers: <input type="text" value="8"/>

### 3.3. Kudo3D Bean

Preliminary printing parameters for Liqcreate Premium White are shown in the table and image below.

For 100 micron / 0.1mm layer thickness:

From Layer	To Layer	Exposure Time (s)	Lift Height (mm)	Lift Speed (mm/min)	Down Speed (mm/min)	Delay Time (s)	
<input type="text" value="1"/>	<input type="text" value="2"/>	<input type="text" value="200"/>	<input type="text" value="8"/>	<input type="text" value="15"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	
<input type="text" value="3"/>	<input type="text" value="5"/>	<input type="text" value="80"/>	<input type="text" value="8"/>	<input type="text" value="15"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	
<input type="text" value="6"/>	<input type="text" value="619"/>	<input type="text" value="12"/>	<input type="text" value="6"/>	<input type="text" value="100"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	

For 50 micron / 0.05mm layer thickness:

From Layer	To Layer	Exposure Time (s)	Lift Height (mm)	Lift Speed (mm/min)	Down Speed (mm/min)	Delay Time (s)	
<input type="text" value="1"/>	<input type="text" value="2"/>	<input type="text" value="200"/>	<input type="text" value="8"/>	<input type="text" value="15"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	
<input type="text" value="3"/>	<input type="text" value="5"/>	<input type="text" value="80"/>	<input type="text" value="8"/>	<input type="text" value="15"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	
<input type="text" value="6"/>	<input type="text" value="619"/>	<input type="text" value="10"/>	<input type="text" value="6"/>	<input type="text" value="100"/>	<input type="text" value="150"/>	<input type="text" value="0.5"/>	

### 3.4. Phrozen Shuffle

Printing parameters for Liqcreate Premium White are shown in the table below.

Slice Thickness (mm)	Exposure Time (s)	Base layers Exposure time (s)	# Base layers
0.100	13	60	8
0.050	11	60	8



Do not store Liqcreate Premium White in PDMS resin trays for extended periods. Resin trays might swell and the PDMS will separate from the plastic bottom. This will not happen in PTFE or high-quality resin trays.



## 4. Post-processing

Post-processing is advised to get the optimal properties out of your prints. This includes rinsing 5 minutes in IPA or (bio)ethanol, preferably ultrasonic or under agitation. Make sure the parts are dry before post-curing, this could be done by placing the parts in a well ventilated area for at least 30 minutes or use pressurized air for 2 minutes. The last step includes curing in a high-power UV curing chamber for 15 minutes at 65 degrees Celsius. Preferred wavelength of the curing unit should be between 300-410nm.

**Caution:** Green parts could break or crack if they are exposed to solvents (bio)ethanol, IPA for longer than 20 minutes.

**Caution:** Green parts need to be completely dry before post-curing. Curing wet and or sticky parts can lead to parts with surface defects.

**Caution:** Using a low-power curing unit can lead to inferior part properties

**Caution:** Always use protective measures when handling liqcreate resins or green parts (Chapter 5). Parts are safe to touch without gloves after proper post-processing.

## 5. Safety

Liqcreate resins and green parts should always be handled with care using the advised precautions such as gloves, glasses and protective clothing. Discard all disposables that have been in contact with resin as chemical waste. Inform the Safety Data Sheet for more information.

### 5.1. Spill cleaning protocol

Spilled resin can be cleaned with standard rinsing solvents like (bio)ethanol or IPA. Treat paper towels with resin as chemical waste.

## 6. Storage and transport

Liqcreate resins should be stored in the original package in a dark and dry area between 5 and 30 degrees Celsius. Close the packaging after every use. For transport the resins should not be exposed to temperatures above 60 degrees Celsius to ensure useability within the expiry date.

## 7. Plastic and Packaging Waste

Fully polymerized Liqcreate products can be treated as plastic waste and are not harmful for the environment. Liquid residue (washing solvent and contaminated papers included) should be treated as chemical waste and disposed as such.

Aluminum packaging can be cleaned by rinsing it with IPA or (bio)ethanol and disposed for recycling. Cardboard packaging should be disposed at a recycling point.